

Broken-Symmetry Ground States of Halogen-Bridged Binuclear Metal Complexes

Shoji Yamamoto

Department of Physics, Okayama University, Tsushima, Okayama 700-8530, Japan
(28 April 1999)

Based on a symmetry argument, we study ground states of what we call MMX-chain compounds, which are the new class of halogen-bridged metal complexes. Commensurate density-wave solutions of a relevant multi-band Peierls-Hubbard model are systematically revealed within the Hartree-Fock approximation. We numerically draw ground-state phase diagrams, where various novel density-wave states appear.

PACS numbers: 71.10.Hf, 71.45.Lr, 75.30.Fv, 03.65.Fd

The competition between electron-electron (el-el) and electron-phonon (el-ph) interactions in one dimension is a fascinating subject to be studied. Halogen-bridged transition-metal linear-chain complexes (MX chains) are good target materials in this context and have a long history of both chemical and physical researches. The mixed-valence MX chains have been attracting extensive interest primarily due to their significant dichroism and unusual Raman spectra [1], while the discovery of the mono-valence MX chains [2–4], whose ground states are Mott insulators instead of Peierls insulators, aroused a renewed interest in this system. These materials, showing the variety of their transition metals, ligands, bridging halogens, and counter ions, enable us to investigate systematically quasi-one-dimensional electronic states [5].

One of the most interesting consequences of intrinsic multi-band effects and competing el-el and el-ph interactions is the variety of ground states. Employing a single-band model discarding the Xp_z orbitals, Nasu [6] visualized highly competing one-dimensional ground states. Extensive and systematic two-band-model study was presented by the Los Alamos group [7–10]. Their vigorous study, covering even incommensurate density waves, re-

vealed various novel phases. Their unique suggestion [11] is also worth mentioning that the MX-chain system can be regarded as a one-dimensional analog of the CuO_2 plane in high- T_c superconductors.

In an attempt to explore further into the family of these materials, new halogen-bridged metal complexes, which are abbreviated as MMX chains, have been synthesized, where binuclear metal units are bridged by halogen ions. $\text{K}_4[\text{Pt}_2(\text{P}_2\text{O}_5\text{H}_2)_4\text{X}] \cdot n\text{H}_2\text{O}$ ($\text{X} = \text{Cl}, \text{Br}, \text{I}$) [12–15] and $\text{M}_2(\text{CH}_3\text{CS}_2)_4\text{I}$ ($\text{M} = \text{Pt}, \text{Ni}$) [16,17] have been attracting considerable attention in the chemical field, whereas they have less been studied in the physical field [18,19] so far. The MMX-chain system may exhibit a wider variety of electronic structures than the MX-chain system. In this letter, focusing on commensurate density-wave ground states, we present a systematic symmetry argument [20–22] and clarify what kinds of broken-symmetry solutions are possible and actually stabilized within the Hartree-Fock (HF) approximation.

In order to treat both M- and X-atom electronic orbitals explicitly, we employ the following one-dimensional model Hamiltonian

$$\begin{aligned} \mathcal{H} = & \sum_{n,s} [(\varepsilon_M - \beta u_{3:n})n_{1:n,s} + (\varepsilon_M + \beta u_{3:n})n_{2:n,s} + \varepsilon_X n_{3:n,s}] + \sum_n K u_{3:n}^2 \\ & - \sum_{n,s} \left[(t_{MX} - \alpha u_{3:n})a_{1:n,s}^\dagger a_{3:n,s} + (t_{MX} + \alpha u_{3:n})a_{2:n,s}^\dagger a_{3:n,s} + t_{MM} a_{1:n,s}^\dagger a_{2:n-1,s} + \text{H.c.} \right] \\ & + \sum_n (U_M n_{1:n,+} n_{1:n,-} + U_M n_{2:n,+} n_{2:n,-} + U_X n_{3:n,+} n_{3:n,-}) \\ & + \sum_{n,s,s'} (V_{MX} n_{1:n,s} n_{3:n,s'} + V_{MX} n_{2:n,s} n_{3:n,s'} + V_{MM} n_{1:n,s} n_{2:n-1,s'}), \end{aligned} \quad (1)$$

where $n_{i:n,s} = a_{i:n,s}^\dagger a_{i:n,s}$ with $a_{1:n,s}^\dagger$, $a_{2:n,s}^\dagger$ and $a_{3:n,s}^\dagger$ being the creation operators of an electron with spin $s = \pm$ (up and down) in the Md_{z^2} and Xp_z orbitals at the n th MXM unit, respectively, and $u_{3:n}$ the chain-direction displacement of the halogen ion from the midpoint between the metal ions at the n th MXM unit. Here we have assumed that the lattice distortion comes only from the halogen ions, which was the case with MX chains with

ligand-locked metal ions. Although metal ions still look locked in the surrounding ligands in the present system, there seems to be an experiment [19] implying movable metal ions in certain MMX chains. However, the present model normally has plenty of parameters to be controlled and therefore we assume fixed metal ions in our first attempt. The momentum representation of the Hamiltonian is generally given by

$$\begin{aligned} \mathcal{H} = & \sum_{i,j} \sum_{k,q} \sum_s \langle i : k + q | t | j : k \rangle a_{i:k+q,s}^\dagger a_{j:k,s} + K \sum_k u_{3:k} u_{3:k}^* \\ & + \frac{1}{2} \sum_{i,j,m,n} \sum_{k,k',q} \sum_{s,t} \langle i : k + q; m : k' | v | j : k; n : k' + q \rangle a_{i:k+q,s}^\dagger a_{m:k',t}^\dagger a_{n:k'+q,t} a_{j:k,s}, \end{aligned} \quad (2)$$

where the spin-free one-body and two-body interactions, $\langle i : k + q | t | j : k \rangle$ and $\langle i : k + q; m : k' | v | j : k; n : k' + q \rangle$, are straightforwardly obtained from the Hamiltonian (1).

Let us introduce the symmetry group of the system as

$$\mathbf{G} = \mathbf{P} \times \mathbf{S} \times \mathbf{T}, \quad (3)$$

where $\mathbf{P} = \mathbf{L}_1 \wedge \mathbf{C}_2$ is the space group of a linear chain with the one-dimensional translation group $\mathbf{L}_1$ whose basis vector is the unit-cell translation l_1 , $\mathbf{S}$ the group of spin rotation, and $\mathbf{T}$ the group of time reversal. Here we have discarded the gauge group arriving at superconducting phases. Group actions on the electron operators are defined as follows [20]:

$$l \in \mathbf{L}_1 : \quad l \cdot a_{i:k,s}^\dagger = e^{-ikl} a_{i:k,s}^\dagger, \quad (4)$$

$$p \in \mathbf{C}_2 : \quad p \cdot a_{i:k,s}^\dagger = a_{i:pk,s}^\dagger, \quad (5)$$

$$u(\mathbf{e}, \theta) \in \mathbf{S} : \quad u(\mathbf{e}, \theta) \cdot a_{i:k,s}^\dagger = \sum_{s'} [u(\mathbf{e}, \theta)]_{ss'} a_{i:k,s'}^\dagger, \quad (6)$$

$$t \in \mathbf{T} : \quad t \cdot (f a_{i:k,s}^\dagger) = -s f^* a_{i:-k,-s}^\dagger, \quad (7)$$

where f is an arbitrary complex number. The spin rotation of angle θ around an axis $\mathbf{e}$, $u(\mathbf{e}, \theta)$, is explicitly represented as $\sigma^0 \cos(\theta/2) - (\boldsymbol{\sigma} \cdot \mathbf{e}) \sin(\theta/2)$ in terms of the 2×2 unit matrix σ^0 and a vector composed of the Pauli-matrices, $\boldsymbol{\sigma} = (\sigma^x, \sigma^y, \sigma^z)$.

Let $\tilde{G}$ denote the irreducible representations of $\mathbf{G}$ over the real number field, where their representation space is spanned by the Hermitian operators $\{a_{i:k,s}^\dagger a_{j:k',s'}\}$. There is a one-to-one correspondence between $\tilde{G}$ and

broken-symmetry phases of density-wave type. Any representation $\tilde{G}$ is obtained as a Kronecker product of the irreducible real representations of $\mathbf{P}$, $\mathbf{S}$, and $\mathbf{T}$:

$$\tilde{G} = \tilde{P} \otimes \tilde{S} \otimes \tilde{T}. \quad (8)$$

$\tilde{P}$ is characterized by an ordering vector q in the Brillouin zone and an irreducible representation of its little group $\mathbf{P}(q)$, and is therefore labeled $q\tilde{P}(q)$. The relevant representations of $\mathbf{S}$ and $\mathbf{T}$ are, respectively, given by

$$\tilde{S}^0(u(\mathbf{e}, \theta)) = 1, \quad \tilde{S}^1(u(\mathbf{e}, \theta)) = O(u(\mathbf{e}, \theta)), \quad (9)$$

$$\tilde{T}^0(t) = 1, \quad \tilde{T}^1(t) = -1, \quad (10)$$

where $O(u(\mathbf{e}, \theta))$ is the 3×3 orthogonal matrix satisfying $u(\mathbf{e}, \theta) \boldsymbol{\sigma}^\lambda u^\dagger(\mathbf{e}, \theta) = \sum_{\mu=x,y,z} [O(u(\mathbf{e}, \theta))]_{\lambda\mu} \boldsymbol{\sigma}^\mu$ ($\lambda = x, y, z$). The representations $\tilde{P} \otimes \tilde{S}^0 \otimes \tilde{T}^0$, $\tilde{P} \otimes \tilde{S}^1 \otimes \tilde{T}^1$, $\tilde{P} \otimes \tilde{S}^0 \otimes \tilde{T}^1$, and $\tilde{P} \otimes \tilde{S}^1 \otimes \tilde{T}^0$ correspond to charge-density-wave, spin-density-wave, charge-current-wave, and spin-current-wave states, respectively. We leave out current-wave states, because in one dimension all of them but one-way uniform-current states break the charge- or spin-conservation law. We consider two ordering vectors $q = 0$ and $q = \pi$, which are labeled Γ and X , respectively. Thus the instabilities labeled $K\tilde{P}(K) \otimes \tilde{S}^i \otimes \tilde{T}^i$ ($K = \Gamma, X$; $i = 0, 1$) are of our interest. Since $\mathbf{P}(\Gamma) = \mathbf{P}(X) = \mathbf{C}_2$, $\tilde{P}(\Gamma)$ and $\tilde{P}(X)$ are either A (C_2 -symmetric) or B (C_2 -antisymmetric) representation of $\mathbf{C}_2$.

In the HF approximation the Hamiltonian (2) is replaced by

$$\mathcal{H}_{\text{HF}} = \sum_{i,j} \sum_{k,s} \sum_{\lambda=0,z} \left[x_{ij}^\lambda(\Gamma; k) a_{i:k,s}^\dagger a_{j:k,s'} + x_{ij}^\lambda(X; k) a_{i:k+\pi,s}^\dagger a_{j:k,s'} \right] \sigma_{ss'}^\lambda. \quad (11)$$

The present model arrives at no helical-spin ($\lambda = x, y$) solution. The self-consistent field $x_{ij}^\lambda(K; k)$ is expressed as

$$\begin{aligned} x_{ij}^0(\Gamma; k) = & \langle i : k | t | j : k \rangle + \sum_{m,n} \sum_{k'} \rho_{nm}^0(\Gamma; k') \\ & \times (2 \langle i : k; m : k' | v | j : k; n : k' \rangle - \langle i : k; m : k' | v | n : k'; j : k \rangle), \end{aligned} \quad (12)$$

$$\begin{aligned} x_{ij}^0(X; k) = & \langle i : k + \pi | t | j : k \rangle + \sum_{m,n} \sum_{k'} \rho_{nm}^0(X; k' + \pi) \\ & \times (2 \langle i : k + \pi; m : k' | v | j : k; n : k' + \pi \rangle - \langle i : k + \pi; m : k' | v | n : k' + \pi; j : k \rangle), \end{aligned} \quad (13)$$

$$x_{ij}^z(\Gamma; k) = - \sum_{m,n} \sum_{k'} \rho_{nm}^z(\Gamma; k') \langle i : k; m : k' | v | n : k'; j : k \rangle, \quad (14)$$

$$x_{ij}^z(X; k) = - \sum_{m,n} \sum_{k'} \rho_{nm}^z(X; k' + \pi) \langle i : k + \pi; m : k' | v | n : k' + \pi; j : k \rangle, \quad (15)$$




FIG. 2. Typical ground-state phase diagrams at various band fillings: (a) $\frac{5}{6}$ band filling, $\alpha = 1.2$, $\beta = 0.6$; (b) $\frac{4}{6}$ band filling, $\alpha = 1.0$, $\beta = 0.5$; (c) $\frac{3}{6}$ band filling, $\alpha = 1.0$, $\beta = 0.5$. Here the following parametrization is common to all the cases: $\varepsilon_M - \varepsilon_X = 1.0$, $V_{MM} = 1.0$, $V_{MX} = 1.0$, and t_{MM} , t_{MX} , and K are all set to unity.

Let us observe a few pieces of numerical investigation. We show in Fig. 2 typical ground-state phase diagrams obtained by computing E_{HF} . As-grown MMX-chain compounds have the $\frac{5}{6}$ -filled band structure, where $q = \pi$ instabilities are dominant unless both U_M and U_X are large enough. Once we go beyond the mean-field theory, the ferromagnetic region should more or less shrink due to multiscattering effects [24]. As holes are doped into the system, $q = \pi$ instabilities are generally replaced by $q = 0$ ones. Further hole doping beyond the $\frac{4}{6}$ band filling again stabilizes $q = \pi$ phases. However, in the heavily hole-doped region where the closed-shell electronic structure of halogen ions is broken, M-SDW with no spin density on halogen sites seems to be much less stabilized. Energy calculations suggest that all the transitions between broken-symmetry phases are of first order. Further numerical investigations, including microscopic information on the electronic structure, will be presented elsewhere. It seems that physical research on MMX-chain compounds is still in its early stage. We hope the present calculation will motivate and accelerate further synthesis and measurements of these fascinating materials.

It is a pleasure to thank H. Okamoto, M. Kuwabara, and K. Yonemitsu for helpful comments and fruitful discussions. This work was supported by the Japanese Ministry of Education, Science, and Culture and the Sanyo-Broadcasting Foundation for Science and Culture. The numerical calculation was done using the facility of the Supercomputer Center, Institute for Solid State Physics, University of Tokyo.

-
- [1] R. J. H. Clark, in *Advances in Infrared and Raman Spectroscopy*, edited by R. J. H. Clark and R. E. Hester (Wiley, New York, 1984) Vol. II, p. 95.
 - [2] H. Toftlund and O. Simonsen, *Inorg. Chem.* **23**, 4261 (1984).
 - [3] K. Toriumi, Y. Wada, T. Mitani, S. Bandow, M. Yamashita, and Y. Fujii, *J. Am. Chem. Soc.* **111**, 2341 (1989).
 - [4] H. Okamoto, T. Mitani, K. Toriumi, and M. Yamashita, *Phys. Rev. B* **42**, 10381 (1990).
 - [5] H. Okamoto, T. Mitani, K. Toriumi, and M. Yamashita, *Mater. Sci. Eng. B* **13**, L9 (1992).
 - [6] K. Nasu, *J. Phys. Soc. Jpn.* **52**, 3865 (1983); **53**, 302 (1984).
 - [7] J. T. Gammel, A. Saxena, I. Batistić, A. R. Bishop, and S. R. Phillpot, *Phys. Rev. B* **45**, 6408 (1992).
 - [8] I. Batistić, J. T. Gammel, and A. R. Bishop, *Phys. Rev. B* **44**, 13228 (1991).
 - [9] H. Röder, A. R. Bishop, and J. T. Gammel, *Phys. Rev. Lett.* **70**, 3498 (1993).
 - [10] A. R. Bishop, *Synth. Met.* **86**, 2203 (1997).
 - [11] J. T. Gammel, K. Yonemitsu, A. Saxena, A. R. Bishop,

and H. Röder, Synth. Met. **55-57**, 3377 (1993).

[12] C.-M. Che, F. H. Herstein, W. P. Schaefer, R. E. Marsh, and H. B. Gray, J. Am. Chem. Soc. **105**, 4604 (1983).

[13] M. Kurmoo and R. J. H. Clark, Inorg. Chem. **24**, 4420 (1985).

[14] R. J. H. Clark, M. Kurmoo, H. M. Dawes, and M. B. Hursthouse, Inorg. Chem. **25**, 409 (1986).

[15] L. G. Butler, M. H. Zietlow, C.-M. Che, W. P. Schaefer, S. Sridhar, P. J. Grunthaner, B. I. Swanson, R. J. H. Clark, and H. B. Gray, J. Am. Chem. Soc. **110**, 1155 (1988).

[16] C. Bellitto, A. Flamini, L. Gastaldi, and L. Scaramuzza, Inorg. Chem. **22**, 444 (1983).

[17] C. Bellitto, G. Dessy, and V. Fares, Inorg. Chem. **24**, 2815 (1985).

[18] N. Kimura, H. Ohki, R. Ikeda, M. Yamashita, Chem. Phys. Lett. **220**, 40 (1994).

[19] H. Kitagawa, T. Sonoyama, M. Yamamoto, T. Mitani, K. Toriumi, and M. Yamashita, to be published in Synth. Met. (1999).

[20] M. Ozaki, Int. J. Quantum Chem. **42**, 55 (1992); S. Yamamoto and M. Ozaki, *ibid.* **44**, 949 (1992).

[21] S. Yamamoto and M. Ozaki, Solid State Commun. **83**, 329 (1992); **83**, 335 (1992).

[22] S. Yamamoto, Phys. Lett. A **247**, 422 (1998).

[23] M. Ozaki, J. Math. Phys. **26**, 1514 (1985).

[24] J. Kanamori, Prog. Theor. Phys. **30**, 275 (1963).

TABLE I. Invariance groups characteristic of each irreducible representation.

Representation	Invariance group
$\Gamma A \otimes \check{S}^0 \otimes \check{T}^0$	$\mathbf{L}_1 \mathbf{C}_2 \mathbf{ST}$
$\Gamma B \otimes \check{S}^0 \otimes \check{T}^0$	$\mathbf{L}_1 \mathbf{ST}$
$XA \otimes \check{S}^0 \otimes \check{T}^0$	$\mathbf{L}_2 \mathbf{C}_2 \mathbf{ST}$
$XB \otimes \check{S}^0 \otimes \check{T}^0$	$(1 + l_1 C_2) \mathbf{L}_2 \mathbf{ST}$
$\Gamma A \otimes \check{S}^1 \otimes \check{T}^1$	$\mathbf{L}_1 \mathbf{C}_2 \mathbf{A}(\mathbf{e}_z) \mathbf{M}(\mathbf{e}_{\parallel})$
$\Gamma B \otimes \check{S}^1 \otimes \check{T}^1$	$(1 + C_2 u(\mathbf{e}_{\parallel}, \pi)) \mathbf{L}_1 \mathbf{A}(\mathbf{e}_z) \mathbf{M}(\mathbf{e}_{\parallel})$
$XA \otimes \check{S}^1 \otimes \check{T}^1$	$(1 + l_1 u(\mathbf{e}_{\parallel}, \pi)) \mathbf{L}_2 \mathbf{C}_2 \mathbf{A}(\mathbf{e}_z) \mathbf{M}(\mathbf{e}_{\parallel})$
$XB \otimes \check{S}^1 \otimes \check{T}^1$	$(1 + l_1 C_2)(1 + l_1 u(\mathbf{e}_{\parallel}, \pi)) \mathbf{L}_2 \mathbf{A}(\mathbf{e}_z) \mathbf{M}(\mathbf{e}_{\parallel})$

$$\mathbf{L}_2 = \{E, l_1^{2n} | n \in \mathbf{N}\}.$$

$$\mathbf{A}(\mathbf{e}_z) = \{u(\mathbf{e}_z, \theta) | 0 \leq \theta \leq 4\pi, \mathbf{e}_z \parallel (\text{the } z \text{ direction})\}.$$

$$\mathbf{M}(\mathbf{e}_{\parallel}) = \{E, tu(\mathbf{e}_{\parallel}, \pi) | \mathbf{e}_{\parallel} \parallel (\text{the chain direction})\}.$$